

POLYURETHANE COATED FELT SUPERFLEX LINER

PRODUCT DESCRIPTION

Polyester fibre single layer flexible Liner with Polyurethane coating custom sized for pipe rehabilitation manufactured in accordance with ISO 9001:2015.

DIMENSION AVAILABILITY

	HOT CURE EVERSION	AMBIENT/WARM CURE EVERSION	HOT CURE DRAG-IN	AMBIENT/WARM CURE DRAG-IN
DIAMETER	50mm to 300mm	50mm to 300mm	50mm to 300mm	50mm to 300mm
THICKNESS	2mm to 3mm	2mm to 3mm	2mm to 3mm	2mm to 3mm
LENGTH	Up to 100m	Up to 100m	Up to 100m	Up to 100m
COATING WEIGHT	125GSM (NOMINAL)			
LINER DESIGN	Liner undersized <10%			
	Liner can negotiate pipe bends up to 90°			

INSTALLATION METHODS

LINER TYPE	RESIN TYPE		CURING REGIME				
	EPOXY	POLYESTER/VINYLESTER	HOT WATER <90°C	STEAM <90°C	AMBIENT	WARM WATER <50°C	WARM AIR ACCELERATED
HOT CURE EVERSION	✗	✗	✗	✗	✓	✓	✓
AMBIENT/WARM CURE EVERSION	✓	✓	✗	✗	✓	✓	✓
HOT CURE DRAG-IN	✗	✗	✗	✗	✓	✓	✓
AMBIENT/WARM CURE DRAG-IN	✓	✓	✗	✗	✓	✓	✓

Note: - Liner must be supported outside the pipe.

TEST SPECIFICATIONS

	CHARACTERISTIC	TEST	STANDARD
ROLL	Density and density distribution at various applied pressures.	Compression measured at increasing pressure.	ISO 845
	Load at break in machine and cross directions.	Tensile testing - Maximum Resistive Force.	ISO 1421
	Secant Modulus in machine and cross directions (resistance to stretch)	Tensile testing - Maximum Resistive Force vs Extension %.	ISO 1421
	Coating weight and distribution.	Samples weighed to determine distribution of coating in cross direction of the roll.	-
	Coating adhesion and ability to weld.	Peel strength of welded tape.	ISO 2411
LINER	Density, Gauge of liner under various applied pressures.	Compression test of sample of all layers.	ISO 845
	Felt weld strengths.	Each weld is sampled and destructively tested.	ISO 1421
	Sealing tape weld strengths.	Each weld is sampled and destructively tested.	ISO 1421

Note: - Liners are manufactured to internal standard or customer specifications. All liners are tested to the tests declared above and adhere to the declared ISO standards. Test data is available on request.

POLYURETHANE COATED FELT SUPERFLEX LINER

CURING TEMPERATURE MAX 90°C

DIAMETER (mm)	LINER THICKNESS (mm)	EVERSION PRESSURE (bar)	MAX EVERSION PRESSURE (bar)	CURING PRESSURE (bar)	MAX PRESSURE (bar) @ 90°C	RESIN AMOUNT (Litre/m)	PINCH ROLLER GAP (mm)
70	2	0.57	0.88	0.57	0.77	0.4	5.5
70	3	0.86	1.32	0.86	1.15	0.6	8.5
100	2	0.40	0.62	0.40	0.54	0.6	5.5
100	3	0.60	0.92	0.60	0.81	0.9	8.0
125	2	0.32	0.49	0.32	0.43	0.7	5.5
125	3	0.48	0.74	0.48	0.65	1.1	8.0
150	2	0.27	0.41	0.27	0.36	0.9	5.5
150	3	0.40	0.62	0.40	0.54	1.3	8.0
200	2	0.20	0.31	0.20	0.27	1.2	5.5
200	3	0.30	0.46	0.30	0.40	1.7	8.0
225	2	0.18	0.27	0.18	0.24	1.3	5.5
225	3	0.27	0.41	0.27	0.36	1.9	8.0
250	2	0.16	0.25	0.16	0.22	1.4	5.5
250	3	0.24	0.37	0.24	0.32	2.2	8.0
275	2	0.15	0.22	0.15	0.20	1.6	5.5
275	3	0.22	0.34	0.22	0.29	2.4	8.0
300	2	0.13	0.21	0.13	0.18	1.7	5.5
300	3	0.20	0.31	0.20	0.27	2.6	8.0

1. Suitable only for BurrowTech Limited liners designed for and to be installed by eversion.
2. Roller gap setting is for guidance only. Impregnation equipment differs: Rubber wrappings on rollers, positional hysteresis and flexing of rollers cause roller gap settings to vary between different equipment. Roller gap setting for any given equipment should be reasonably repeatable.
3. We strongly recommend the resin addition be monitored and controlled by adjustment of the roller gap setting. Ultimately, it is the correct resin addition which is imperative, not the roller gap.
4. All information is provided by BurrowTech Limited in good faith, but without warranty. All calculations should be verified.